

聯塑烯 UNITHENE®

高密度聚乙烯塑膠原料

High Density Polyethylene Resins

LH506



特性

聯塑烯 LH506，為射出成型級的高密度聚乙烯，具備優異的抗衝擊強度與改良之抗外界應力龜裂性，極適合於射製各種運動器具、工業用箱等，並且可利用乾式混合或擠壓熔混的方式輕易地染成各種顏色。

Characteristics

UNITHENE LH506 is a high density polyethylene (HDPE) developed for injection molding applications. Possessing outstanding impact strength and improved resistance to environmental stress, UNITHENE LH506 is specially suitable for molding sport utensils and industrial cases. UNITHENE LH506 could be easily pigmented to any color by either dry blending or extrusion homogenization of pigment into the resin.

應用

1. 射出成型

Applications

1. injection molding

物理性質 Physical Properties

項目 Properties	試驗方法 Test Method	數 值 Typical Value
密度 Density (g/cm ³)	ASTM D1505	0.955
熔融指數 Melt Index (g/10min)	ASTM D1238	5.5
降伏點抗張強度 Tensile Strength (Yield) (kg/cm ²)	ASTM D638	250
斷裂點抗張強度 Tensile Strength (Break) (kg/cm ²)	ASTM D638	290
斷裂點伸長率 Ultimate Elongation (%)	ASTM D638	760
抗衝擊強度 Izod Impact Strength(kg-cm/cm)	ASTM D256	11
彈性係數(模片) 1% Secant Modulus(Molded) (kg/cm ²)	ASTM D638	8,400
扭轉剛性 Torsional Stiffness (kg/cm ²)	ASTM D1043	10,000
彎曲剛性 Flexural Stiffness (kg/cm ²)	ASTM D747	9,200
抗低溫脆裂性 Low Temperature Brittleness(°C/F50)	ASTM D746	<-76
衛氏軟化溫度 Vicat Softening Point(°C)	ASTM D1525	125
熔點 Melt Point (°C)	USI Method	132
硬度(蕭氏 D)Hardness (Shore D)	ASTM D2240	68

據本公司所知，上述資料應屬正確無誤，惟因使用時之情況非受本公司管制，所以本公司對上述所作之一切建議，恕不負保證之責。
The information contained herein is, to our best knowledge, true and accurate. However, since conditions of use are beyond our control, all risks of such use are assumed by users.

USI Corporation 台灣聚合化品股份有限公司

Tel:886-2-87516888 Fax:886-2-26599599 Web:www.usife.com.tw E-mail:service_usi@tpe.usife.com.tw

Address:12th Floor, No.37 Ji Hu Road, Nei Hu District, Taipei 114, Taiwan 地址:台北市 114 內湖區基湖路 37 號 12 樓