

THENE[®]

低密度聚乙烯塑膠原料 Low Density Polyethylene Resins NA205-15



特性

百塑烯 NA205-15 是一種低密度聚乙烯，專為不同材質，如紙張、玻璃紙、鋁箔、聚烯烴膜、多元酯膜及尼龍膜而發展的擠壓塗膠 PE 塑膠。

NA205-15 對於不同材質也擁有良好的黏著性，例如對紙張的黏著力跟非多孔性材料如玻璃紙、鋁箔一樣好。

NA205-15 的防潮性很好，加上良好的熱封性，是極佳的塗膠材料。

NA205-15 加工性及流動性良好，塗膠邊緣皺縮少，而且能高速塗膠並可減少塗膠過程中的損失。

應用

1. 擠壓塗膠

Characteristics

PAXOTHENE NA205-15 (LDPE) is specially developed for extrusion coating on various substrates such as paper, cellophane, aluminum foil, polyolefin film, polyester film and nylon film.

NA205-15 also possesses excellent adhesion to a variety of porous substrates such as paper as well as non-porous substrates such as cellophane and foil. Low moisture-vapor transmission rates in combination with excellent heat sealability makes NA205-15 a good coating material.

Concerning processability, good flow characteristics and low neck-in of NA205-15 provide high line speed and reduce the loss of resin in the extrusion coating.

Applications

1. Extrusion Coating

物理性質 Physical Properties

項目 Properties	試驗方法 Test Method	數 值 Typical Value
密度 Density (g/cm ³)	ASTM D1505	0.919
熔融指數 Melt Index (g/10min)	ASTM D1238	3.0
降伏點抗張強度(薄膜) (kg/cm ²) Yield Point Tensile Strength (Film) MD/TD	ASTM D882	92/92
斷裂點抗張強度(薄膜) (kg/cm ²) Break Point Tensile Strength (Film) MD/TD	ASTM D882	195/157
斷裂點伸長率(薄膜) (%) Ultimate Elongation(Film) MD/TD	ASTM D882	330/540
抗衝擊強度*(落下實驗)克/半數破壞 Impact Strength(Dart Drop) g/F50*	ASTM D1709	98
混濁度/光澤度(60°) Haze/Gloss(60°)	ASTM D1003/D523	6.0/100
抗低溫脆裂性 Low Temperature Brittleness(°C/F50)	ASTM D746	<-76
衛氏軟化溫度 Vicat Softening Point(°C)	ASTM D1525	100
熔點 Melt Point (°C)	DSC	109
硬度(蕭氏 D)Hardness (Shore D)	ASTM D2240	53

據本公司所知，上述資料應屬正確無誤，惟因使用時之情況非受本公司管制，所以本公司對上述所作之一切建議，恕不負保證之責。
The information contained herein is, to our best knowledge, true and accurate. However, since conditions of use are beyond our control, all risks of such use are assumed by users

USI Corporation 台灣聚合化品股份有限公司

Tel:886-2-87516888 Fax:886-2-26599599 Web:www.usife.com.tw E-mail:service_usi@tpe.usife.com.tw

Address:12th Floor, No.37 Ji Hu Road, Nei Hu District, Taipei 114, Taiwan 地址:台北市 114 內湖區基湖路 37 號 12 樓