

線塑烯 LINATHENE®

線性低密度聚乙烯塑膠原料

Linear Low Density Polyethylene Resins

LL120C



特性

線塑烯 LL120C 為鑄膜擠壓專用的線型低密度聚乙烯，用來製作薄膜具有高韌度、高抗張強度、高伸長率、極佳的耐穿刺強度及光學性質等優點，適合製作伸縮包裝膜、保鮮膜、農業用膜。

Characteristics

LINATHENE LL120C is a butene linear low density polyethylene(LLDPE) developed for slot cast film extrusion.

Films made from LINATHENE LL120C have excellent toughness, tensile strength, elongation, puncture strength and transparency.

LINATHENE LL120C is recommended for the manufacture of stretch film, cling film and agricultural film.

應用

1. 鑄模擠壓

Applications

1. Casting

物理性質 Physical Properties

項目 Properties	試驗方法 Test Method	數 值 Typical Value
密度 Density (g/cm ³)	ASTM D1505	0.919
熔融指數 Melt Index (g/10min)	ASTM D1238	2.0
降伏點抗張強度 yield point Tensile Strength (kg/cm ²) (MD/TD)	ASTM D882	105/95
斷裂點抗張強度 Tensile Strength at break (kg/cm ²) (MD/TD)	ASTM D882	240/170
斷裂點伸長率 Elongation at break (%) (MD/TD)	ASTM D882	500/600
抗衝擊強度*(落下實驗)克/半數破壞 Impact Strength(Dart Drop) g/F50*	ASTM D1709	110
抗低溫脆裂性 Low Temperature Brittleness(°C/F50)	ASTM D746	< -76
衛氏軟化溫度 Vicat Softening Point(°C)	ASTM D1525	102
熔點 Melt Point (°C)	USI Method	122

據本公司所知，上述資料應屬正確無誤，惟因使用時之情況非受本公司管制，所以本公司對上述所作之一切建議，恕不負保證之責。
The information contained herein is, to our best knowledge, true and accurate. However, since conditions of use are beyond our control, all risks of such use are assumed by users.

USI Corporation 台灣聚合化品股份有限公司

Tel:886-2-87516888 Fax:886-2-26599599 Web:www.usife.com.tw E-mail:service_usi@tpe.usife.com.tw

Address:12th Floor, No.37 Ji Hu Road, Nei Hu District, Taipei 114, Taiwan 地址:台北市 114 內湖區基湖路 37 號 12 樓